

Draft Sri Lanka Standard
SPECIFICATION FOR EMULSION PAINTS FOR EXTERIOR USE
(Second Revision)

DSLS 557 :

Gr.

Copyright Reserved
SRI LANKA STANDARDS INSTITUTION
17, Victoria Place,
Elvitigala Mawatha,
Colombo 8,
Sri Lanka.

Draft Sri Lanka Standard
SPECIFICATION FOR EMULSION PAINTS FOR EXTERIOR USE
(Second Revision)

FOREWORD

This Sri Lanka Standard was approved by the Sectoral Committee on Chemical and Polymer Technology and was authorized for adoption and publication as a Sri Lanka Standard by the Council of the Sri Lanka Standards Institution on.....

Emulsion paints have gained popularity for characteristics such as ease of application, quick drying properties, non-objectionable odour and good washability. In these paints water is used for thinning instead of organic solvents. As far as emulsion paints for exterior use are concerned, weathering resistance is the one of the most important criterion.

This Standard was first published in 1982 and First Revision was issued in 2009. This Second Revision is issued to incorporate amendments brought to **SLS 557:2009** and to introduce new test method for determination of drying time and resistance to alkali. In this revision the test panels of asbestos have been replaced by non asbestos panel and changed the number of cycles for determination of scrub resistance. Accelerated method have been introduced for determination of resistance to fungus.

This Standard is subject to the restrictions imposed under the Consumer Affairs authority Act No. 09 of 2003 and any other relevant Acts.

For the purpose of deciding whether a particular requirement of this Specification is complied with, the final value, observed or calculated, expressing the result of a test or an analysis, shall be rounded off in accordance with **SLS 102**. The number of significant places retained in the rounded off value shall be the same as that of the specified value in this Specification.

1 SCOPE

This Specification prescribes the requirements and methods of sampling and tests for emulsion paints used for exterior decoration on buildings after surface preparation and priming wherever necessary.

2 REFERENCES

| | | |
|--------|------|--|
| ASTM D | 1308 | Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes |
| ASTM D | 2486 | Standard Test Methods for Scrub Resistance of Wall Paints and |
| ASTM D | 5590 | Standard Test Method for Determining the Resistance of Paint Films Related Coatings to Fungal Defacement by Accelerated Four-Week Agar Plate Assay |

| | | |
|------------|------|--|
| ASTM D | 5895 | Standard Test Methods for Evaluating Drying or Curing During Film Formation of Organic Coatings Using Mechanical Recorders |
| SLS | 102 | Rules for rounding off numerical values |
| SLS | 489 | Glossary of terms for paints |
| SLS | 523 | Methods of sampling of paints, varnishes and raw materials for paint and varnishes |
| SLS | 1256 | Methods of test for paints and varnishes Part 3 Determination of viscosity at a high rate of shear Part 6 Determination of quantity of material in a container Part 11 Standard panels for testing Part 13 Determination of hard drying time Part 25 Guidance on the conduct of natural weathering tests Part 28 Exposure to laboratory light sources – General guidance and fluorescent UV lamps Part 30 Determination of surface drying time ballotini method |
| SLS ASTM D | 3335 | Standard Test Method for Low Concentrations of Lead, Cadmium and Cobalt in Paint by Atomic Absorption Spectrometry |

3 DEFINITIONS

For the purpose of this Specification, the definitions given in **SLS 489** shall apply.

4 REQUIREMENTS

4.1 Composition

The material shall be a medium consisting of any stable synthetic polymer emulsion in water containing pigments and applicable additives to produce a material so as to satisfy the requirements of this Specification.

4.2 Conditions of the material in the container

The material shall be free from lumps, loose skins, extraneous matter and colour separation. If any settlement is observed, the paint shall be capable of being readily re dispersed with a spatula to a smooth homogeneous state. The material shall not have irritating or offensive odour.

4.3 Thinning

As per manufacturer's instructions paint shall be thinned with water. The paint shall mix readily with a minimum amount of foaming to a smooth and homogeneous state. Foaming if any, shall dissipate rapidly.

4.4 Application properties

The material after thinning shall be suitable for application by brush, spray, roller or any other method specified by the manufacturer. The resulting film shall have uniform leveling characteristics and shall not show pigment flocculation and coarseness or other undesirable characteristics.

4.5 Recoating properties

As per manufacturer's instructions paint shall be thinned with water and applied three successive coats of the material at 50 °C on a non asbestos flat cement sheet at an interval of 30 minutes between successive coatings, there shall be no lifting of the underlying coats. The paint film coatings shall not exhibit colour change, sagging, cracking or flaking after application.

4.6 Keeping properties (Before open the container)

The paint when stored under normal storage and temperature condition in the original sealed container shall retain the properties as prescribed in Clause 4 requirements for the specified period which is not less than 1 year. The material shall also be free from any extraneous matter such as fungal and bacterial growth and non objectionable odour.

4.7 Quantity of material

The volume of the material shall be tested as prescribed in **SLS 1256: Part 6** at 27 ± 2 °C. The measured volume shall be within a tolerance of ± 5 per cent and ± 2 per cent from the declared volume for the containers up to 5 litre and above 5 litre respectively.

4.8 Colour

The colour of the product shall match with the Standard colour or any reference colour as agreed to between the purchaser and the manufacturer when tested as prescribed in Appendix B.

4.9 Spreading capacity

The spreading capacity shall be determined as prescribed in Appendix C. The minimum spreading capacity shall be 14 m²/litre. Volume of the material applied shall be determined as in 4.7.

4.10 Resistance to artificial weathering

When the paint film is prepared and tested in accordance with the methods given in **SLS 1256: Part 28: Section 1** and **SLS 1256: Part 28: Section 2** there shall be no considerable change in colour, loss of gloss, blistering and cracking of the paint film.

4.11 Resistance to alkali

The coating shall not show cracking, peeling, wrinkling, chalking and other visual defects when tested and examined as prescribed in method 1 of Appendix D. The material shall be

deemed to have complied with this requirement when tested and examined as prescribed in method 2 of Appendix D.

4.12 Resistance to fungal and algal growth

The coated panels shall be free from surface fungal and algal growth when tested as both methods prescribed in Appendix E.

4.13 Lead content

The total lead content of the paint material shall be less than 90 mg/kg when tested as prescribed in SLS ASTM D 3335.

4.14 Other requirements

The material shall also comply with the requirements given in Table 1 when tested in accordance with the methods given in Column (4) of the table.

TABLE 1 – Other requirements for emulsion paints for exterior use

| Sl. No. | Characteristic | Requirement | Method of test |
|---------|--|--|---------------------------|
| (1) | (2) | (3) | (4) |
| i) | Drying time, max. a) Surface dry, minutes b) Hard dry, h | 15 2 | Appendix F |
| ii) | Viscosity at 25 ±2 °C Pa s, min. | 0.4 | SLS 1256 Part 3 |
| iii) | Finish | Smooth and matt or gloss | Appendix F |
| iv) | pH value, at 27 ±2 °C | 7 to 9 | Appendix G |
| v) | Scrub resistance | 800 cycles (matt) 1500 cycles (gloss) | ASTM D 2486 (Method A) |
| vi) | Temperature stability | To pass the test | Appendix H |

5 PACKAGING AND MARKING

5.1 Packaging

The material shall be packed in sound, clean, dry, leakage free and corrosion resistant containers. The volume of the material shall be as agreed between the manufacturer and the purchaser.

5.2 Marking

Each container shall be marked legibly and indelibly with the following:

- a) Type of the product as “Emulsion paint for exterior use”;
- b) Colour;
- c) Name and address of the manufacturer including the country of origin;
(**NOTE** *Name and address of the manufacturer and the distributor need to be marked on imported products.*)
- d) Brand name if any;
- e) Net volume of the material in litre;
- f) Date of manufacture;
- g) Shelf life / best before;
- h) Batch number or code number or lot identification number;
(**NOTE:** *if one batch is manufactured during the day date of manufacture may be used as the batch no. /lot identification no. / code no.*)
- j) Spreading capacity, in m²/litre;
- k) Registered trade mark if any;
- l) Declared lead content;
(**NOTE:** *If marked as “lead free”, it shall be based on the test results of each batch.*)
- m) Instructions for use;
- n) Special precautions to be obtained in use if required; and
- o) Specific warning statement(s), where necessary.

6 METHOD OF TEST

6.1 Tests shall be carried out as prescribed in 4.5, Appendices B to H, ASTM D 1308, ASTM D 2486, ASTM D 5590, ASTM D 5895, SLS ASTM D 3335 and the relevant sections of SLS 1256.

6.2 During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

APPENDIX A COMPLIANCE OF A LOT

The sampling scheme given in this Appendix shall apply where compliance of a lot to the requirements of this Specification has to be assessed based on statistical sampling and inspection.

Where compliance with this Specification, appropriate schemes of sampling and inspection shall be adopted based on manufacturer’s control systems coupled with type tests and testing procedures.

A.1 LOT

In any consignment, all the containers of same size containing paint material of one batch of manufacture shall constitute a lot.

A.2 SAMPLING

The method of drawing representative samples of the material shall be as specified in the relevant clauses of **SLS 523**.

A.3 NUMBER OF TESTS

A.3.1 Each container selected as in **A.2** shall be inspected for packaging and marking requirements.

A.3.2 From each of the sample container prepared as in clause **5.2** of **SLS 523**, a small but equal quantity of material shall be taken and mixed thoroughly to form a composite sample. The composite sample shall be transferred to another sample container.

A.3.3 The remaining portion of material from each sample container shall constitute an individual sample representing a particular container in the lot.

A.3.4 Tests for requirements given in **4.1** to **4.7** shall be carried out on each individual sample.

A.3.5 Tests for requirements given in **4.8** to **4.14** shall be carried out on the composite sample.

A.4 CRITERIA FOR CONFORMITY

The material shall be taken as conformed to the Specifications if the following conditions are satisfied:

A.4.1 Each container inspected as in **A.3.1** satisfies the packaging and marking requirements.

A.4.2 Each individual sample shall satisfy the relevant requirements tested as in **A.3.4**.

A.4.3 The composite sample shall satisfy the relevant requirements tested as in **A.3.5**.

APPENDIX B DETERMINATION OF COLOUR

B.1 PRINCIPLE

The colour of the material applied on a white unglazed art paper is compared visually in diffused daylight with that of the standard or agreed colour as appearing on the colour card provided by the relevant manufacturer.

B.2 PROCEDURE

B.2.1 Apply the material using a film applicator as specified in **SLS 1256 : Part 11 : Section 2** to give a wet film thickness of 50 µm on a 150 -mm x 150-mm white unglazed art paper. Air-dry the film for 4 hours in a well ventilated room in a horizontal position. During drying protect the film from direct sunlight. When the film is dry, apply a second coat of the material to give again a combined wet film thickness of 50 µm and air-dry. After 24 hours, compare the colour of the film with that of the standard or previously agreed colour visually in diffused daylight.

B.2.2 The material shall be deemed to have passed the test if the colour of the material matches with the colour card provided by the relevant manufacturer.

APPENDIX C DETERMINATION OF SPREADING CAPACITY

C.1 PROCEDURE

Weigh an appropriate quantity of the material with a suitable brush. The material shall then be applied without diluting using with a one inch brush to a flat, smooth and non-absorbent surface of 100 cm² in area in a uniform normal coat commensurate with satisfactory coverage and appearance. The balance of the material with the brush shall be weighed.

The spreading rate shall be calculated as the number of square meters that can be covered by one litre of the paint.

The spreading capacity is given as the average spreading rate.

APPENDIX D DETERMINATION OF RESISTANCE TO ALKALI

Two methods have been prescribed for the determination of resistance to alkali. The method prescribed in **D.1** shall be the reference method and shall be carried out in case of any dispute.

D.1 METHOD 1

D.1.1 This test shall be carried out as prescribed in **ASTM D 1308**.

D.2 METHOD 2 (LIME BURNING TEST)

D.2.1 Principle

The material is applied to non asbestos cement panel and the bleaching effect examined. In order to give a basis for comparison, one half of the panel is sealed with alkali resistant solvent based primer.

D.2.2 Materials

D.2.2.1 Non asbestos cement panel, 300-mm x 100-mm size flat sheet and having a pH not less than 10

D.2.2.2 Phthalocyanine blue pigment paste, prepared using phthalocyanine pigment

D.2.3 Procedure

D.2.3.1 Select a 300-mm x 100-mm non asbestos cement panel having a pH of not less than 10 and condition it at 27 ± 2 °C for one hour. Seal one half of the same with one coat of an alkali-resistant solvent-based primer, by brushing. Apply the material with a 400- μ m film applicator as specified in **SLS 1256 : Part 11: Section 2** to the entire panel. If the material is not coloured, it should be tinted to a light blue shade using suitable phthalocyanine pigment paste, before application. Leave coating until dry and when dry examine the panel for difference in colour between the sealed and the unsealed halves.

D.2.3.2 The material shall be deemed to have passed the test if the colour difference between the unsealed and the sealed halves is not appreciable when examined visually.

APPENDIX E

DETERMINATION OF RESISTANCE TO FUNGAL AND ALGAL GROWTH

E.1 METHOD 1- RESISTANCE TO FUNGAL AND ALGAL GROWTH

E.1.1 Principle

A flat non asbestos cement panel is evenly coated with two coats of the material by brushing and then air dried for a specified period. The panel is exposed on an exposure rack for a specified period and the intensity of fungal growth is observed.

E.1.2 Apparatus

E.1.2.1 Exposure rack

The exposure rack shall be constructed as specified in **SLS 1256: Part 25** to support the panel vertically and facing toward the equator.

E.1.3 Procedure

Apply two coats of the paint by brushing as specified in **SLS 1256 : Part 11 : Section 2** on a 300-mm x 150-mm x 4-mm clean, dry, untreated flat non asbestos cement panel (see **D.2.2.1**) at an interval 30 minutes drying between coats. The edges and back of the panels shall be coated with a protective paint. Expose the panels on the exposure rack and examine the fungal and algae growth on the panels monthly, for six months.

E.2 METHOD 2- RESISTANCE TO FUNGAL GROWTH

E.2.1 This test shall be carried out as prescribed in **ASTM D 5590**

APPENDIX F
DETERMINATION OF DRYING TIME AND APPEARANCE OF DRIED FILM
(FINISH)

Two methods have been prescribed for each of the determination for surface drying and hard drying times. The method prescribed in **F.1** shall be the reference method and shall be carried out in case of any dispute.

F.1 METHOD 1

F.1.1 Determination of surface drying time (Ballotini method)

This test shall be carried out as prescribed in **SLS 1256: Part 30**.

F.1.2 Determination of hard drying time

This test shall be carried out as prescribed in **SLS 1256: Part 13**.

F.2 METHOD 2

F.2.1 Surface drying time and hard drying time shall be determined as prescribed in **ASTM D 5895**.

F.3 APPEARANCE OF DRIED FILM (FINISH)

The second coat of the material shall be applied satisfactorily at the end of 4 hours of the first coating. Examine the panel for surface dry and hard dry after 15 minutes and 2 hours respectively. The material shall be deemed to have complied with the requirement of this standard for finish if the composite film gives a smooth and matt or gloss finish.

APPENDIX G
DETERMINATION OF pH

G.1 PRINCIPLE

The material is mixed with freshly boiled water to remove the Carbon dioxide and the Hydrogen ion concentration is measured using a calibrated pH meter.

G.2 PROCEDURE

Weigh 5.00 ± 0.01 g of the material. Place it in a 150-ml beaker and add 50 g of freshly boiled, distilled water. Mix well by means of a glass rod and cool to 27 ± 2 °C. Measure the pH with a pH meter using glass electrodes.

APPENDIX H DETERMINATION OF TEMPERATURE STABILITY

H.1 PRINCIPLE

The material is subjected to extremes of temperature and then tested for thinning and application properties.

H.2 PROCEDURE

H.2.1 Fill two clean, dry 500-ml metal containers with the material leaving the usual ullage and seal tightly. Keep one of the containers at 10 ± 1 °C and the other at 60 ± 2 °C for 48 hours. Keep these two containers at room temperature for 24 hours thereafter. Subsequently, examine the material in the two containers.

H.2.2 The material shall be deemed to have passed this test if it is free from lumps, skins, settling and is capable of thinning suitably for application method specified by manufacturer.

.....