

**AMENDMENT NO. 1 APPROVED ON 1981-07-28.****CS 68 : 1969 SPECIFICATION FOR WROUGHT ALUMINIUM SHEET AND STRIP USED IN THE MANUFACTURE OF UTENSILS**

Delete the existing tables and substitute the following tables.

**TABLE 1 - Tensile strength of aluminium of grade I**

Condition	Tensile strength (Mega pascals)		Elongation on 50 mm gauge length
	Min.	Max.	
Annealed	-	100	30
¼ Hard	93	116	12
½ Hard	108	131	7
¾ Hard	124	147	5
Hard	139	-	3

**TABLE 2 - Tensile strength of aluminium of grade II**

Condition	Tensile strength (Mega pascals)		Elongation on 50 mm gauge length
	Min.	Max.	
Annealed	-	116	30
¼ Hard	116	147	12
½ Hard	139	170	7
¾ Hard	162	193	5
Hard	178	-	3